



Bs-Temperature

H=1194A/m



Initial permeability	μ_i	25°C	3200±25%
Saturation magnetic flux density	Bs(mT)	25°C	530
		100°C	420
Remanence	Br(mT)	25°C	130
		100°C	80
Coercivity	Hc(A/m)	25°C	11
		100°C	10
		25°C	350






Electrical resistivity	$\rho(\Omega\cdot m)$	3
Density	d(kg/m³)	4.8×10^3

Test core : Toroid(mm)


OD : 25

ID : 15

H : 7.5



μ_i -Frequency



B-H

