


Initial permeability	μ_i	25°C	3000±25%
Saturation magnetic flux density	Bs(mT)	25°C	530
		100°C	425
Remanence	Br(mT)	25°C	100
		100°C	75
Permeability	$\mu_r(\%)$	25°C	15
		100°C	12
Core loss	Pcv(kW/m ³)	0°C	380
		25°C	330
		100°C	350
		120°C	380



Curie temperature	Tc(°C)	≥225
Electrical resistivity	$\rho(\Omega\cdot m)$	4
Density	d(kg/m ³)	4.8×10 ³

